

# BALTIC BROWN



**CUARCITA**  
DE VENEIRA



# BALTIC BROWN

## TECHNICAL SPECIFICATIONS

<b>Petrographic denomination</b>	Rapakivi granite	UNE-EN 12407
<b>Apparent density</b>	2690 Kg/m <sup>3</sup>	UNE-EN 1936
<b>Open porosity</b>	0.4%	UNE-EN 1936
<b>Water absorption</b>	0.2%	UNE-EN 13755
<b>Abrasion resistance</b>	15.8 mm.	UNE-EN 14157
<b>Breaking load at dowel hole</b>	2000 N.	UNE-EN 13364
<b>Compressive strenght</b>	143 MPa	UNE-EN 1926
<b>Flexural strenght</b>	9.7 Mpa	UNE-EN 12372
<b>Frost resistance (Decrease of Rf after 48 cycles)</b>	9.7 %	UNE-EN 12371
<b>Slip resistance</b>	Polished: 83/13 SRV Honed: 67/20 SRV	UNE-EN 14231

### **Cuarcitas Aveneira S.L.**

Veneira de Roques  
27336 A Pobra do Brollon (Lugo - España)  
**Teléfono:** + 34 982 530 053  
**Fax:** + 34 982 530 347  
**E-mail:** info@cuarcitadeveneira.com

### **Delegación en Argelia**

Rue Mouloud Zadi, 7 - 1 Et.  
Sacre Coeur - Alger  
**Tfnos.**  
00213 554965992  
00213 552330117